

HM Wire International, Inc.
 Ph: 330-244-8501 Fax: 330-244-8561
 www.litz-wire.com info@litz-wire.com www.hmwire.com



AISI 1075 Carbon Steel

Nominal Composition:	C%	Mn%	P%	S%
	0.70 - 0.80	0.40 - 0.70	4%	5%

Applications: Design Engineers use Aisi 1075 Carbon Steel for springs or cutting tools.

Physical Properties

English Units	
Specific Gravity	7.86
Specific Heat	0.107 Btu/lb/Deg F - [32 - 212 Deg F]
Melting Point	2760 °F
Density	.284 lb / cu. in. @68 °F
Poissons Ratio	0.3
Thermal Conductivity	360
Mean Coeff Thermal Expansion	6.7
Modulus of Elasticity (Tension)	30 psi x 10 ⁶
Modulus of Torsion	11 x 10 ⁶

Mechanical Properties

English Units	
Rockwell Hardness	C24 - 33