

# HM Wire International, Inc.

Ph: 330-244-8501 Fax: 330-244-8561

www.litz-wire.com info@litz-wire.com www.hmwire.com

REQUEST  
A  
QUOTATION

## Alloy 201 - Nickel Alloy

**Description:** Alloy 201 is commercially pure wrought Nickel and prevents embrittlement by intergranular carbon at elevated temperatures.

**Applications:** Soap, viscose rayon, vinyl chloride monomer.

Nominal Composition:	C	Mn	Si	Cu	S	Kg	Ni	Fe
	0.02	0.35	0.35	0.25	0.01	0.05	99.0	0.4

## Physical and Mechanical Properties

	Metric Units
Density	8.9 gm/cu cm
Specific Heat	440 J/kg K
Electrical Resistivity	8.5 micro ohms cm
Melting Range	1435 - 1445°C
Thermal Expansion (10 <sup>-6</sup> K)	14.3 (20 - 300°C)
<b>Yield Strength</b>	<b>Rp 0.2%</b>
20°C Temp	80N/mm sq
100°C Temp	70N/mm sq
200°C Temp	65N/mm sq
300°C Temp	60N/mm sq
400°C Temp	55N/mm sq
<b>Tensile Strength</b>	<b>RM</b>
	45N/mm sq
<b>Elongation</b>	<b>A5 min</b>
	40%

\*To be used as a guideline only.

Copyright ©2011 HM Wire International

R1.06.13.2011