

HM Wire International, Inc.

Ph: 330-244-8501 Fax: 330-244-8561

www.litz-wire.com info@litz-wire.com www.hmwire.com

Fluorinated Ethylene Propylene (FEP), Molded/Extruded

Electrical Properties	Metric	English
Electrical Resistivity	1.00e + 18 ohm-cm	1.00e + 18 ohm-cm
Dielectric Constant	2.00 - 2.20	2.00 - 2.20
Dielectric Strength	20.0 - 24.0 kV/mm	508 - 610 kV/in
Dissipation Factor	0.0000600 - 0.000500	0.0000600 - 0.000500

Some of the values displayed may have been converted from their original units and/or rounded in order to display the information in a consistent format. To be used as a guideline only. TEFLON® is a registered trademark of DuPont.

Copyright HM Wire International 2009

Rev 1.11032009