

HM Wire International, Inc.

Ph: 330-244-8501 Fax: 330-244-8561

www.litz-wire.com info@litz-wire.com www.hmwire.com

Fluorinated Ethylene Propylene (FEP), Molded/Extruded

Mechanical Properties	Metric	English
Hardness, Shore D	55.0	55.0
Tensile Strength	19.0 - 22.0 Mpa	2760 - 3190 psi
Ultimate Elongation at Break	250 - 330 %	250 - 330 %
Modulus of Elasticity	0.343 Gpa	49.7 ksi
Flexural Modulus	0.539 - 0.637 Gpa	78.2 - 92.4 ksi
Compressive Yield Strength	5.00 - 6.00 Mpa	725 - 870 psi
Izod Impact, Unnotched	NB	NB
Coefficient of Friction	0.0400 - 0.0600	0.0400 = 0.0600
Coefficient of Friction, Static	0.0500	0.0500
Taber Abrasion, mg/1000 Cycles	0.000 - 96.0	0.000 - 96.0

Some of the values displayed may have been converted from their original units and/or rounded in order to display the information in a consistent format. To be used as a guideline only. TEFLON® is a registered trademark of DuPont.

Copyright HM Wire International 2009

Rev 1.11032009