

HM Wire International, Inc.

Ph: 330-244-8501 Fax: 330-244-8561

www.litz-wire.com info@litz-wire.com www.hmwire.com

Fluorinated Ethylene Propylene (FEP), Molded/Extruded

Optical Properties	Metric	English
Transmission, Visible	92.0 - 95.0 %	92.0 - 95.0 %
IR Transmittance	95.0 - 98.0 %	95.0 - 98.0 %
UV Transmittance	91.0 - 92.0 %	91.0 - 92.0 %

Some of the values displayed may have been converted from their original units and/or rounded in order to display the information in a consistent format. To be used as a guideline only. TEFLON® is a registered trademark of DuPont.

Copyright HM Wire International 2009

Rev 1.11032009