

HM Wire International, Inc.

Ph: 330-244-8501 Fax: 330-244-8561

www.litz-wire.com info@litz-wire.com www.hmwire.com

Fluorinated Ethylene Propylene (FEP), Molded/Extruded

Physical Properties	Metric	English
Bulk Density	0.530 - 1.20 g/cc	0.0191 - 0.0434 lb/in ³
Density	1.30 - 2.17 g/cc	0.0470 - 0.0784lb/in ³
Solids Content	23.0 - 50.0 %	23.0 - 50.0 %
Water Absorption	0.0100%	0.0100%
Oxygen Transmission	1/50e - 7 cc-mm/m ² - 24hr - atm	3.81e - 7 cc-mm/m ² - 24hr - atm
Nitrogen Transmission	9.00e - 7 cc-mm/m ² - 24hr - atm	.00000229 - 7 cc-mm/m ² - 24hr - atm
Viscosity	0.0100 - 4.00e+7 cP	0.0100 - 4.00e+7 cP
Thickness	12.7 - 5000 microns	0.500 - 197 mil
Linear Mold Shrinkage	0.0300 - 0.0600 cm/cm	0.0300 - 0.0600 in/in
Melt Flow	0.800 - 37.0 g/10 min	0.800 - 37.0 g/10 min
Deformation	3.00 - 5.00 %	3.00 - 5.00 %

Some of the values displayed may have been converted from their original units and/or rounded in order to display the information in a consistent format. To be used as a guideline only. TEFLON® is a registered trademark of DuPont.

Copyright HM Wire International 2009

Rev 1.11032009