

# HM Wire International, Inc.

Ph: 330-244-8501 Fax: 330-244-8561

www.litz-wire.com info@litz-wire.com www.hmwire.com

## Fluorinated Ethylene Propylene (FEP), Molded/Extruded

Thermal Properties	Metric	English
CTE, Linear	83.0 - 105 $\mu\text{m}/\text{m}\cdot^{\circ}\text{C}$	46.1 - 58.3 $\mu\text{in}/\text{in} - ^{\circ}\text{F}$
Thermal Conductivity	0.250 W/m-K	1.74 BTU-in/hr - $\text{ft}^2 - ^{\circ}\text{F}$
Melting Point	245 - 275 $^{\circ}\text{C}$	473 - 527 $^{\circ}\text{F}$
Maximum Service Temperature, Air	200 $^{\circ}\text{C}$	392 $^{\circ}\text{F}$
Flammability, UL94	V-0	V-0
Oxygen Index	95.0%	95.0%

Some of the values displayed may have been converted from their original units and/or rounded in order to display the information in a consistent format. To be used as a guideline only. TEFLON® is a registered trademark of DuPont.

Copyright HM Wire International 2009

Rev 1.11032009