

HM Wire International, Inc.

Phone: 330-244-8501 Fax: 330-244-8561

www.litz-wire.com info@litz-wire.com www.hmwire.com

Mechanical Properties for Types 302, 304 & 316L

The minimum tensile strength for straightened and cut lengths shall be 90% of the values listed in the table. Spring Temper values are in accordance with ASTM A-313.

Finished Diameter (Inches)	Type 302 and 304		Type 316L	
	Spring Temper (KSI)		Spring Temper (KSI)	
	Min	Max	Min	Max
Up to .009 in.	325	355	245	275
Over .009 to .010	320	350	245	275
Over .010 to .011	318	348	240	270
Over .011 to .012	316	346	240	270
Over .012 to .013	314	344	240	270
Over .013 to .014	312	342	240	270
Over .014 to .015	310	340	240	270
Over .015 to .016	308	338	235	265
Over .016 to .017	306	336	235	265
Over .017 to .018	304	334	235	265
Over .018 to .020	300	330	235	265
Over .020 to .022	296	326	235	265
Over .022 to .024	292	322	235	265
Over .024 to .026	291	320	235	265
Over .026 to .028	289	318	235	265
Over .028 to .031	285	315	235	265
Over .031 to .034	282	310	235	265
Over .034 to .037	280	308	235	265
Over .037 to .041	275	304	235	265
Over .041 to .045	272	300	230	260
Over .045 to .050	267	295	230	260
Over .050 to .054	265	293	225	255
Over .054 to .058	261	289	220	250
Over .058 to .063	258	285	220	250
Over .063 to .070	252	281	215	245
Over .070 to .075	250	278	215	245
Over .075 to .080	246	275	210	240
Over .080 to .087	242	271	205	235
Over .087 to .095	238	268	205	235
Over .095 to .105	232	262	200	230