

HM Wire International, Inc.
 Ph: 330-244-8501 Fax: 330-244-8561
 www.litz-wire.com info@litz-wire.com www.hmwire.com



Nichrome 60 & 62 / 16

Nominal Data Sheet

Nominal Composition

Chromium:	16.0%
Iron:	Balance
Silicone	1.5%
Nickel:	60.0%

Typical Mechanical Properties for Annealed Wire

Ultimate Tensile Strength		200,000 lb/in ²	Hard Drawn
Specific Resistance		675 Ohms per Circular Mil foot at 68°F	
Elongation in 2" *		20%	
Specific Gravity		8.25%	

Physical Properties

Density		0.2979 lbs/cu/in
Melting Point (approx.)		1350°C
Electrical Resistivity @ RT		112 Microm ² cm
Temperature Coefficient of Resistivity (20° to 500°C)		0.00015 Ohms
Linear Expansion Coefficient (20° to 1000°C)		17.5 x 10 ⁶ / °C
Thermal Conductivity @ 100°C		0.132 W/cm/°C
Magnetic Attraction		Para

To be used as a guideline only.

Copyright HM Wire ©2011

R1. 04.20.11